

5100-4900				5300-5100			
Typical specifications (will vary from mine to mine)				Typical specifications (will vary from mine to mine)			
ASPECT	DETAIL	TYPICAL	REJECT	ASPECT	DETAIL	TYPICAL	REJECT
	ADB/GAD	5100	4900		ADB/GAD	5300	5100
	ARB/GAR	3500	3200		ARB/GAR	4000	3700
	NCV/NAR	3300	3000		NCV/NAR	3800	3500
Total Moisture	ARB	39.00%	47.00%	Total Moisture	ARB	37.00%	42.00%
Inherent moisture	ADB	17.00%	21.00%	Inherent moisture	ADB	16.00%	19.00%
Ash Content	ADB	6.00%	11.00%	Ash Content	ADB	6.00%	10.00%
Volatile Matter	ADB	around 35-45%		Volatile Matter	ADB	around 35-45%	
Fixed Carbon	ADB	by difference		Fixed Carbon	ADB	by difference	
Total Sulphur	ADB	up to 0.8%	over 1%	Total Sulphur	ADB	up to 0.8%	over 1%
HGI		around 50 to 70		HGI		around 50 to 70	
Size	0--50	around 85-90%		Size	0--50	around 85-90%	
5500-5300				5800-5600			
Typical specifications (will vary from mine to mine)				Typical specifications (will vary from mine to mine)			
ASPECT	DETAIL	TYPICAL	REJECT	ASPECT	DETAIL	TYPICAL	REJECT
	ADB/GAD	5500	5300		ADB/GAD	5800	5600
	ARB/GAR	4300	4100		ARB/GAR	5100	4900
	NCV/NAR	4000	3800		NCV/NAR	4900	4700
Total Moisture	ARB	33.00%	36.00%	Total Moisture	ARB	23.00%	27.00%
Inherent moisture	ADB	15.00%	18.00%	Inherent moisture	ADB	13.00%	17.00%
Ash Content	ADB	8.00%	12.00%	Ash Content	ADB	11.00%	14.00%
Volatile Matter	ADB	around 35-45%		Volatile Matter	ADB	around 35-45%	
Fixed Carbon	ADB	by difference		Fixed Carbon	ADB	by difference	
Total Sulphur	ADB	up to 0.8%	over 1%	Total Sulphur	ADB	up to 0.8%	over 1%
HGI		around 45 to 60		HGI		around 40 to 55	
Size	0--50	around 85-90%		Size	0--50	around 85-90%	
6000-5800				6300-6100			
Typical specifications (will vary from mine to mine)				Typical specifications (will vary from mine to mine)			
ASPECT	DETAIL	TYPICAL	REJECT	ASPECT	DETAIL	TYPICAL	REJECT
	ADB/GAD	6000	5800		ADB/GAD	6300	6100
	ARB/GAR	5400	5100		ARB/GAR	5800	5600
	NCV/NAR	5100	4800		NCV/NAR	5500	5300
Total Moisture	ARB	18.00%	21.00%	Total Moisture	ARB	16.00%	18.00%
Inherent moisture	ADB	9.00%	12.00%	Inherent moisture	ADB	9.00%	12.00%
Ash Content	ADB	8.00%	14.00%	Ash Content	ADB	12.00%	15.00%
Volatile Matter	ADB	around 35-45%		Volatile Matter	ADB	around 35-45%	
Fixed Carbon	ADB	by difference		Fixed Carbon	ADB	by difference	
Total Sulphur	ADB	up to 1%	over 1%	Total Sulphur	ADB	up to 1%	over 1%
HGI		around 40 to 50		HGI		around 40 to 50	
Size	0--50	around 85-90%		Size	0--50	around 85-90%	

6500-6300				6800-6500			
Typical specifications (will vary from mine to mine)				Typical specifications (will vary from mine to mine)			
ASPECT	DETAIL	TYPICAL	REJECT	ASPECT	DETAIL	TYPICAL	REJECT
	ADB/GAD	6500	6300		ADB/GAD	6800	6500
	ARB/GAR	6000	5800		ARB/GAR	6500	6300
	NCV/NAR	5800	5600		NCV/NAR	6200	6000
Total Moisture	ARB	12.00%	16.00%	Total Moisture	ARB	9.00%	11.00%
Inherent moisture	ADB	6.00%	10.00%	Inherent moisture	ADB	5.00%	9.00%
Ash Content	ADB	10.00%	13.00%	Ash Content	ADB	10.00%	13.00%
Volatile Matter	ADB	around 35-45%		Volatile Matter	ADB	around 35-45%	
Fixed Carbon	ADB	by difference		Fixed Carbon	ADB	by difference	
Total Sulphur	ADB	up to 1%	over 1%	Total Sulphur	ADB	up to 1%	over 1%
HGI		around 40 to 60		HGI		around 40 to 50	
Size	0--50	around 85-90%		Size	0--50	around 85-90%	
7100-6800				7300-7100			
Typical specifications (will vary from mine to mine)				Typical specifications (will vary from mine to mine)			
ASPECT	DETAIL	TYPICAL	REJECT	ASPECT	DETAIL	TYPICAL	REJECT
	ADB/GAD	7100	6800		ADB/GAD	7300	7100
	ARB/GAR	6800	6600		ARB/GAR	7000	6800
	NCV/NAR	6500	6300		NCV/NAR	6800	6600
Total Moisture	ARB	8.00%	11.00%	Total Moisture	ARB	7.00%	11.00%
Inherent moisture	ADB	5.00%	8.00%	Inherent moisture	ADB	4.00%	8.00%
Ash Content	ADB	10.00%	13.00%	Ash Content	ADB	6.00%	10.00%
Volatile Matter	ADB	around 35-45%		Volatile Matter	ADB	around 35-45%	
Fixed Carbon	ADB	by difference		Fixed Carbon	ADB	by difference	
Total Sulphur	ADB	up to 1%	over 1%	Total Sulphur	ADB	up to 1%	over 1%
HGI		around 40 to 70		HGI		around 40 to 70	
Size	0--50	around 85-90%		Size	0--50	around 85-90%	